



CARFIL QUALITY
YOUR SUPPLIER FOR ALL LABORATORY NEEDS

Carfil Litaspen



Features

Material	Poplar
Appearance	Fine wood chips
Average particle size	2,5 - 3,5 mm
Bulk density	140 - 200 g/L
Dust content (< 200μ)	< 0,1 %
Moisture	6 %
Water absorbency*	Average 295 %
Absorption speed**	40 sec
pH-value	7,3
Packaging:	
Standard	- Autoclavable bag of 10 kg - 36 bags per plastic europalet
Irradiation 10 kGy	- Sealed, double packaging of 10 kg - 36 bags per plastic europalet

*100 ml beaker glass, filling up to 15 ml + 10 ml water

** (output weight sieve mass) / mass*100 = water binding capacity



PAVAN SERVICE BVBA

Beyntellus 3 - B-2360 Oud-Turnhout - Tel. +32 (0)14 45 13 10 - admin@carfil.be - BTW BE 0420.681.872

www.carfil.be