



CARFIL QUALITY
YOUR SUPPLIER FOR ALL LABORATORY NEEDS

Carfil Litaspen 2



Features

Material	Poplar
Appearance	Very fine wood chips
Average particle size	1,4 - 1,0 mm
Bulk density	145 - 210 g/L
Dust content (< 200μ)	0,2 %
Moisture	8 %
Water absorbency*	Average 390 %
Absorption speed**	30 sec
pH-value	7,3
Packaging:	
Standard	- Autoclavable bag of 10 kg - 39 bags per plastic europalet
Irradiation 10 kGy	- Sealed, double packaging of 10 kg - 39 bags per plastic europalet

*100 ml beaker glass, filling up to 15 ml + 10 ml water

** (output weight sieve mass) / mass*100 = water binding capacity



PAVAN SERVICE BVBA

Beyntellus 3 - B-2360 Oud-Turnhout - Tel. +32 (0)14 45 13 10 - admin@carfil.be - BTW BE 0420.681.872

www.carfil.be